

# MATERIAL DATA SHEET

RHEINZINK-prePATINA  
graphite grey



- **NATURAL SURFACE**
- **PICKLING PROCESS  
CREATES THE LOOK  
OF PATINA**
- **SELF-HEALING OF  
SCRATCH MARKS**
- **100% RECYCLABLE**

## BASIS-INFORMATION

---

The RHEINZINK-prePATINA product line is the only one on the market with a natural surface that is neither coated nor painted. The color effect is rather a result of the metal alloy itself. A higher copper content allows a darker surface to be created in the unique RHEINZINK-preweathering process. As the inventors, we called this production method "pre-weathering" and have coined the word to this day. In this way, the colour "graphite grey" can be produced ex works, which is caused by its higher copper content, while the later natural patina formation will have a slightly greenish colour change.

Specific weight 7.2 g/cm<sup>3</sup>

Building material class A1 (non-combustible)

Titanium zinc according to DIN EN 988

Certified according to QUALITY ZINC, TÜV Rheinland

Meets ASTM B69-16 Architectural Rolled Zinc Type 2

## DELIVERY FORMS

---

Standard widths	500-1000 mm
Standard thicknesses	0.70 – 0.80 mm
Protective film	On request
Coil inner diameter	508 mm at > 500 kg 400 mm at < 500 kg

## IMPORTANT INSTALLATION INSTRUCTIONS

---

Bending radius	Minimum 1.75 mm from 1.00 mm on 1.75 x t
Soldering recommendation	Soldering flux "ZD-pro (company Felder), Overlap area 10 to 15 mm
Processing temperature	Warming up in temperatures below 10°
Protective film	Remove the film immediately after assembly

*Note:*

*In the event of contamination due to external or environmental influences, please request the RHEINZINK cleaning recommendations. With these recommendations, RHEINZINK cannot guarantee that a new look will be created.*

# MATERIAL DATA SHEET

RHEINZINK-prePATINA  
graphite grey

GRAPHITIE GREY

prePATINA graphite grey

## ALLOY

---

Zinc	99.995% (Z1 according to DIN EN 1179)
Copper	0.80 – 1.00%
Titanium	0.06 – 0.12%
Aluminum	≤ 0.015%

## CERTIFICATION

---

Quality management	Certified according to ISO 9001
Environmental management	Certified according to ISO 14001
Energy management	Certified according to ISO 50001
Environmental product declaration	Verified according to ISO 14025, TYPE III and EN 15804

External monitoring 4 times per year by TÜV Rheinland

## MECHANICAL-TECHNOLOGICAL PROPERTIES

---

0.2% proof stress (Rp0.2)	≥ 115 N/ mm <sup>2</sup>
Tensile strength (Rm)	≥ 160N/ mm <sup>2</sup>
Breaking elongation (A50)	≥ 45%
Vickers hardness (HV3)	≥ 45
Folding test	No cracks on the bending edge
Bending up after folding test	No cracks after bending up
Fold tensile force test*	D ≥ 0.7
Erichsen cupping	≥ 8.0 mm
Longitudinal curvature	≤ 1.0 mm/ m
Flatness	≤ 1.5 mm wave height
Permanent elongation in creep (Rp0.1)	≤ 0.1%

\*D = (tensile strength of folding sample) / (tensile strength of material)

## PHYSICAL AND CHEMICAL PROPERTIES

---

Melting point / range	420 °C
Boiling point / range	906 °C
Recrystallization limit	> 300 °C
Density at 20 °C	7.2 g/ cm <sup>3</sup>
Elasticity modulus	≥ 80.000 N/ mm <sup>2</sup>
Expansion coefficient	
In the longitudinal direction	22·10 <sup>-6</sup> K <sup>-1</sup>
In the rolling transverse	17·10 <sup>-6</sup> K <sup>-1</sup>
Thermal conductivity	110 W/ m · K
Specific heat capacity	398 J/ kg/ K
Electrical conductivity	17 m/Ω · mm <sup>2</sup>
Viscosity	Dynamic at 500 °C: 0.0030 mPa·s